

Technical Data Sheet

Marlex[®] HHM TR-144

This high molecular weight hexene copolymer is designed for film applications. It has been formulated to provide....

- Good processability
- Good toughness and durability
- Good blending characteristics with HDPE HMW film resin

Typical applications include:

- Multi wall liners
- T-shirt & shopping bags
- Trash bags

This resin meets these specifications:

FDA Regulation 21CFR 177.1520. Suitable for food packaging.

Nominal Physical Properties *	ASTM	Unit	Value
Density	D1505	g/cm ³	0.946
Melt Index, Condition 190°C/ 2.16 kg HLMI, Condition 190°C/21.6 kg	D1238 D1238	g/10min g/10min	0.18 15
Flexural Modulus, Tangent	D790	MPa	1150
Brittleness Temperature	D746	°C	<-75
<u>Typical Film Properties</u> ** Dart Drop (66cm)	D1709	g	90
Spencer Impact Strength	D3420	J	0.35
Tensile Yield Strength, 50 mm/min	D882	MPa	MD: 24 TD: 26
Elongation at Break, 50 mm/min	D882	%	MD: 480 TD: 640
Elmendorf Tear Strength	D1922	g	MD: 19 TD: 270

* The nominal properties reported herein are typical of the product, but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded. The physical properties were determined on compression molded specimens that were prepared in accordance with Procedure C of ASTM D4703, Annex A1. **Based on 0.025 mm film produced at 4:1 blow-up ratio.

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in que stion and is further a dvised against relying on the information contained herein as it m ay relate to a ny specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Qa tar Chemical Company Ltd does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly a ssumes a ll risk and l iability, whether b ased in contact, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as any international laws which m ay be encountered in the use thereof. S uch questions should be investigated by the user.

For more information:

Qatar Chemical Company LTD (Q-Chem) P.O. Box 24646 Doha - Qatar Tel: (+974) 44847110 (+974) 44847111 Email: marketing@qchem.com.qa

> MSDS (+974) 44847110 OR Visit our site www.qchem.com.qa

> > Revised July 2011